

TechGeo DURABILITY LLDPE SMOOTH 1.00 mm

TechGeo DURABILITY LLDPE SMOOTH Geomembrane series was developed to overcome international standards and recommendations and aims to offer greater durability and enable a longer service life for the projects when specified.

Manufactured by a Blown Film process using latest generation virgin resins and additives **TechGeo DURABILITY LLDPE SMOOTH** has greater durability compared to standard market geomembranes.

In addition, it has greater elongation, high mechanical resistance and excellent chemical resistance.

Available sizes	
Width (m)	Length (m)
7.00	100

PROPERTIES	TEST METHOD	UNITY	1.00 mm 40 mils	TESTING FREQUENCY
Thickness (min.ave.)	ASTM D5199	mm	Nominal	Per roll
Formulated Density (min.)	ASTM D1505/D792	g/cm ³	0.939	90,000 kg
Tensile Properties – Break strength (min.ave.)	ASTM D6693 Type IV	kN/m	27	9,000 kg
Tensile Properties – Break elongation (min.ave.)	ASTM D6693 Type IV	%	800	
2% Modulus (max.)	ASTM D5323	N/mm	420	Per formulation
Tear resistance (min.ave.)	ASTM D1004	N	100	20,000 kg
Puncture resistance (min.ave.)	ASTM D4833	N	250	20,000 kg
Axi-Symmetric Break Resistance Strain - % (min.)	ASTM D5617	%	30	Per formulation
Carbon Black Content	ASTM D1603	%	2 - 3	20,000kg
Carbon Black Dispersion	ASTM D5596	-	Note (1)	20,000 kg
Oxidative Induction Time Standard OIT (min.ave.)	ASTM D3895	min	125	90,000kg
High Pressure OIT (min.ave.)	ASTM D5885		600	
Oven Aging *	ASTM D5721	%	35	Per formulation
Standard OIT (min.ave.)	ASTM D3895			
High Pressure OIT (min.ave.)	ASTM D5885			
UV Resistance **	ASTM D7238	%	Note (2) 45	Per formulation
Standard OIT (min.ave.)	ASTM D3895			
High Pressure OIT (min.ave.)	ASTM D5885			

(1) Carbon black dispersion for 10 different views: 9 in categories 1 and 2; 1 in category 3

(2) Not recommended since the high temperature of the Standard OIT test produces an unrealistic result for some of the antioxidants in the UV exposed samples

Obs: roll tolerable variation in width and length: ±2%

* (Retained after 90 days)

** (Retained after 1.600hrs)